

Process for making high temperature resistant foam sheets of polysulfones or polyethersulfones

Publication number: EP1333051

Publication date: 2003-08-06

Inventor: DIETZEN FRANZ-JOSEF DR (DE); SCHERZER
DIETRICH DR (DE); QUEISSER JOACHIM DR (DE);
RUECK SWEN (DE); EHRMANN GERD DR (DE);
KRATZMUELLER WOLFGANG (DE)

Applicant: BASF AG (DE)

Classification:

- International: C08J9/12; C08J9/00; C08J9/00; (IPC1-7): C08L81/06;
C08J9/14; C08J9/00

- european: C08J9/00K55

Application number: EP20020027251 20021206

Priority number(s): DE20011062602 20011220

Also published as:



US7045082 (B2)
US2006125136 (A1)
US2004212119 (A1)
JP2003192818 (A)
EP1333051 (A3)

more >>

Cited documents:



US5017622
US4275186

Report a data error here

Abstract of EP1333051

Water, or a mixture (pts. wt.) of water (100) and organic liquid (at most 200) is used as the blowing agent in a method for the production of foam sheet by extruding a mixture of polysulfone or polyethersulfone and volatile blowing agent (1-10 wt.%) under pressure at above 300 degreesC into the open air.

Data supplied from the esp@cenet database - Worldwide

03. Dez. 2002

1

Korrigierter Text

Production of foam webs from high-temperature-resistant polysulfones or polyether sulfones

5 The invention relates to a process for producing foam webs from a polysulfone or a polyether sulfone by extruding a mixture of the thermoplastic with from 1 to 10% by weight of a volatile blowing agent, under pressure into the open atmosphere.

10 A process of this type is described in DE-A 4 207 257. Blowing agents used there are oxygen-containing aliphatic liquids, such as alcohols, ketones, esters, and ethers, in particular acetone. However, a problem arising is that the use of these readily combustible liquids represents a considerable safety risk at the
15 high temperatures used.

It is an object of the present invention to eliminate this risk or at least to reduce it.

20 We have found that this object is achieved by using, as blowing agent, water or a mixture of water with up to 200 parts by weight, based on 100 parts by weight of water, of an inert gas or organic liquid as ancillary blowing agent.

25 The blowing agent is water or else a mixture with the following ancillary blowing agents

- inert gases, such as CO₂, nitrogen, argon,
- hydrocarbons, such as propane, butane, pentane, hexane,
- 30 - aliphatic alcohols, such as methanol, ethanol, propanol, isopropyl alcohol, butanol,
- aliphatic ketones, such as acetone or methyl ethyl ketone,
- aliphatic esters, such as methyl or ethyl acetate,
- fluorohydrocarbons (e.g. 134a, 152a),
- 35 - a mixture of these.

Particular preference is given to water, and also to mixtures of water with up to 100 parts by weight, based on 100 parts by weight of water, of an alcohol or of a ketone with a boiling
40 point between 50 and 100°C.

The amounts used of the blowing agent are from 1 to 10% by weight, preferably from 2 to 8% by weight, based on the thermoplastics. It is possible to add conventional auxiliaries,
45 e.g. nucleating agents, to regulate the number of cells.

1. REF
Übersetzung Auslandstext für PCT
(Nationale Phase) Europa + National
Bitte kontrollieren und zurück an AST bis
Danke
2. AST

2

Surprisingly, it has been found that foam webs of particularly low density are obtained if the polymer used comprises a mixture of a high-molecular-weight and a low-molecular-weight polysulfone or polyether sulfone, preferably in a mixing ratio of from 5:1 to 1:5. It is preferable here for the flowability MVR 360°C/10 kg to ISO 1133 of the high-molecular-weight polymer to be below 75 [cm³/10 min], and that of the low-molecular-weight polymer to be greater than 80 [cm³/10 min].

- 10 The process of the invention is preferably carried out on a plant composed of two extruders. In the first extruder, the thermoplastic is firstly melted at above its glass transition temperature, then the blowing agent is injected into the melt under pressure and homogeneously mixed with the same, whereupon
15 the glass transition temperature of the mixture falls. In the second extruder, the mixture is cooled to a temperature at which the viscosity of the melt is still sufficiently high to form a good foam. Finally, the mixture is extruded into the open atmosphere, whereupon it foams. If a slot die is used, the foam
20 sheets obtained preferably have a thickness of from 0.5 to 8 cm and a density of from 30 to 100 g/l.

The proportions of materials mentioned in the example are percentages by weight.

25

Example 1

The foam specimens were extruded on a tandem plant. This is composed of a melting extruder and a cooling extruder.

30

- A polyether sulfone (ULTRASON 2010 from BASF AG) is fed to the first extruder. The polymer is melted, and the blowing agent or the mixture of the blowing agent is injected and then mixed into the melt, the temperature of which is 340°C. The melt comprising
35 blowing agent is then cooled in the second extruder to the temperature needed for foaming (see table). After discharge from a slot die, the melt foams and is shaped in a calibrator to give sheets.

40

45

3

| Experiment | H ₂ O (%) | Acetone (%) | ST (°C) | Thickness (mm) | Density (g/l) |
|------------|----------------------|-------------|---------|----------------|---------------|
| 1 | | 5 | 246.5 | 11 | 46 |
| 2 | 1 | 4 | 249.1 | 11 | 43 |
| 3 | 2 | 3 | 249.4 | 10 | 46 |
| 4 | 2 | 2 | 248.7 | 10 | 52 |
| 5 | 3 | 1 | 248.1 | 10 | 63 |
| 6 | 2 | | 243.8 | 10 | 82 |
| 7 | 2 | | 247.8 | 10 | 124 |
| 8 | 1.5 | | 250.2 | 10 | 178 |

Experiments 1 and 2 are non-inventive.

15 Example 2

As described in Example 1, foam sheets were produced from polyether sulfone. Instead of a single grade, a mixture composed of a free-flowing, low-viscosity PES (low molecular weight) and a low-flowability, high-viscosity PES (high molecular weight) was foamed.

The materials used are PES E1010, E2010, and E3010 from BASF.

25 The following MFR values describe the flowability of these materials.

| | MVR 360°C/10 kg (cm ³ /10 min) ISO 1133 |
|-------|--|
| E1010 | 150 |
| E2010 | 77 |
| E3010 | 40 |

35 The mixture of grades has broad molecular weight distribution and can be foamed with water as sole blowing agent to give lower densities than those given by the individual components.

| | E1010 (%) | E2010 (%) | E3010 (%) | H ₂ O (%) | Density (g/l) |
|-----|-----------|-----------|-----------|----------------------|---------------|
| 100 | | | | 3 | 84 |
| | | 100 | | 3 | 82 |
| | | | 100 | 3 | 98 |
| 67 | | | 33 | 3 | 66 |

We claim

1. A process for producing foam webs by extruding a mixture of a
5 polysulfone or polyether sulfone and from 1 to 10% by weight,
based on the thermoplastics, of a volatile blowing agent,
under pressure at above 300°C into the open atmosphere, which
comprises using, as blowing agent, water or a mixture of
water with up to 200 parts by weight, based on 100 parts by
10 weight of water, of an inert gas or organic liquid as
ancillary blowing agent.
2. A process as claimed in claim 1, wherein the blowing agent is
water or a mixture of water with up to 100 parts by weight,
15 based on 100 parts by weight of water, of an alkanol or of an
aliphatic ketone with boiling point between 50 and 100°C.
3. A process as claimed in claim 1, wherein use is made of a
mixture of a high-molecular-weight and a low-molecular-weight
20 polysulfone or polyether sulfone.

25

30

35

40

45

5

Production of foam webs from high-temperature-resistant polysulfones or polyether sulfones

5 Abstract

The invention relates to a process for producing foam webs by foam extrusion of a mixture of a polysulfone or polyether sulfone and a volatile blowing agent, where the blowing agent is water or
10 a mixture of water with an inert gas or organic liquid, e.g. an alcohol or a ketone.

15

20

25

30

35

40

45